



SABIC® LLDPE 218WJ

LINEAR LOW DENSITY POLYETHYLENE

DESCRIPTION

218WJ is a butene Linear Low Density Polyethylene TNPP free grade suitable for general purpose packaging. It is easy to process giving good tensile properties, impact strength and optical properties. 218WJ contains slip and antiblock additives.

TYPICAL APPLICATIONS

Lamination film, thin liners, shopping bags, carrier bags, garbage bags, coextruded films, consumer packaging and other general-purpose applications.

TYPICAL PROPERTY VALUES

Revision 20170716

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate			
at 190°C and 2.16 kg	2	g/10 min	ASTM D1238
Density	918	kg/m ³	ASTM D1505
FORMULATION			
Slip agent	<input checked="" type="checkbox"/>	-	-
Anti block agent	<input checked="" type="checkbox"/>	-	-
MECHANICAL PROPERTIES			
Dart Impact Strength	85	g/μm	ASTM D1709
OPTICAL PROPERTIES			
Haze ⁽¹⁾	13	%	ASTM D1003
Gloss			
at 60°	80	-	ASTM D2457
FILM PROPERTIES			
Tensile Properties			
stress at break, MD	35	MPa	ASTM D882
stress at break, TD	29	MPa	ASTM D882
strain at break, MD	700	%	ASTM D882
strain at break, TD	750	%	ASTM D882
stress at yield, MD	12	MPa	ASTM D882
stress at yield, TD	10	MPa	ASTM D882
1% secant modulus, MD	220	MPa	ASTM D882
1% secant modulus, TD	260	MPa	ASTM D882
Puncture resistance	63	J/m	SABIC method

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Elmendorf Tear Strength			
MD	130	g	ASTM D1922
TD	320	g	ASTM D1922
THERMAL PROPERTIES			
Vicat Softening Point	98	°C	ASTM D1525

(1) Mechanical properties have been measured by producing 30 µ film with 2.5 BUR using 100% 218NJ.

PROCESSING CONDITIONS

Typical processing conditions for 218WJ are:
Melt temperature: 185 - 205°C, Blow up ratio: 2.0 - 3.0

HEALTH, SAFETY AND FOOD CONTACT REGULATIONS

218WJ resin is suitable for Food contact application. Detailed information is provided in relevant Material Safety Datasheet and for additional specific information please contact SABIC local representative for certificate.

DISCLAIMER: This product is not intended for and must not be used in any pharmaceutical/medical applications.

STORAGE AND HANDLING

Polyethylene resin should be stored in a manner to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably do not exceed 50°C. SABIC would not give warranty to bad storage conditions which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process PE resin within 6 months after delivery.

DISCLAIMER

The information contained herein may include typical properties of our products or their typical performances when used in certain typical applications. Actual properties of our products, in particular when used in conjunction with any third party material(s) or for any non-typical applications, may differ from typical properties.

It is the customer's responsibility to inspect and test our product(s) in order to satisfy itself as to the suitability of the product(s) for its and its customers particular purposes. The customer is responsible for the appropriate, safe and legal use, processing and handling of all product(s) purchased from us.

Nothing herein is intended to be nor shall it constitute a warranty whatsoever, in particular, warranty of merchantability or fitness for a particular purpose.

SABIC as referred to herein means any legal entity belonging to the group of companies headed by Saudi Arabia Basic Industries Corporation.