

# PETLIN LD C150Y

Low Density Polyethylene  
**PETLIN (MALAYSIA) SDN BHD**



## Technical Data

### Product Description

PETLIN LD C150Y is a low density polyethylene resin for general purpose and film applications. It is produced by the state-of-the-art DSM Stamicarbon tubular process. It contains antioxidant (BHT free), slip and antiblock additives. It is intended primarily for blown film process.

### General

Material Status	• Commercial: Active		
Literature <sup>1</sup>	• <a href="#">Technical Datasheet (English)</a>		
Availability	• Asia Pacific		
Additive	• Antioxidant	• High Antiblock	• High Slip
Features	• Antioxidant • Food Contact Acceptable • Good Drawdown	• Heat Sealable • High Antiblocking • High Clarity	• High Gloss • High Slip • Low Gel
Uses	• Bags • Film	• Foam • Laundry Bags	
Agency Ratings	• FDA 21 CFR 177.1520		
Forms	• Pellets		
Processing Method	• Blown Film	• Film Extrusion	

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	0.921 g/cm <sup>3</sup>	0.921 g/cm <sup>3</sup>	ISO 1183/A
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	5.0 g/10 min	5.0 g/10 min	ISO 1133

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Coefficient of Friction	0.10	0.10	ASTM D1894

Films	Nominal Value (English)	Nominal Value (SI)	Test Method
Film Thickness - Tested	0.98 mil	25 µm	
Film Thickness - Recommended / Available	150 to 60 µm	150 to 60 µm	
Tensile Modulus			ISO 527-3
MD: 0.98 mil (25 µm)	29300 psi	202 MPa	
TD: 0.98 mil (25 µm)	32500 psi	224 MPa	
Tensile Stress			ISO 527-3
MD: Break, 0.98 mil (25 µm)	3770 psi	26.0 MPa	
TD: Break, 0.98 mil (25 µm)	2180 psi	15.0 MPa	
Tensile Elongation			ISO 527-3
MD: Break, 0.98 mil (25 µm)	150 %	150 %	
TD: Break, 0.98 mil (25 µm)	610 %	610 %	
Dart Drop Impact (0.98 mil (25 µm))	86 g	86 g	ASTM D1709
Elmendorf Tear Strength			ISO 6383-2
MD: 0.98 mil (25 µm)	18000 lbf	80000 N	
TD: 0.98 mil (25 µm)	6700 lbf	30000 N	

Optical	Nominal Value (English)	Nominal Value (SI)	Test Method
Gloss (45°, 0.984 mil (25.0 µm))	66	66	ASTM D2457
Haze (0.984 mil (25.0 µm))	6.5 %	6.5 %	ASTM D1003

Extrusion	Nominal Value (English)	Nominal Value (SI)
Melt Temperature	293 to 329 °F	145 to 165 °C

### Notes

<sup>1</sup> These links provide you with access to supplier literature. We work hard to keep them up to date; however you may find the most current literature from the supplier.

<sup>2</sup> Typical properties: these are not to be construed as specifications.

## PETLIN LD C150Y

Low Density Polyethylene

**PETLIN (MALAYSIA) SDN BHD**

---

### Where to Buy

---

#### Supplier

**PETLIN (MALAYSIA) SDN BHD**

Kuala Lumpur, Malaysia

Telephone: 60-3-2051-7908

Web: <http://www.petronas.com.my/>

---


#### Distributor

Please contact the supplier to find a distributor for PETLIN LD C150Y

---



Founded in 1986 and based in Laramie, Wyoming, IDES is now part of the UL family of companies. UL is a premier global independent safety science company with more than a century of proven history. Employing nearly 10,000 professionals in over 100 countries, UL has five distinct business units -- Product Safety, Environment, Life & Health, Knowledge Services and Verification Services -- to meet the expanding needs of our customers and to deliver on our public safety mission.



### Prospector Plastics Database - [www.ides.com/prospector](http://www.ides.com/prospector)

Prospector is a searchable online database that includes 85,000 data sheets from 875 manufacturers and 44,000 UL yellow cards. Each data sheet includes property, processing and supplier contact information. Prospector is relied on by nearly 400,000 design engineers and plastics processors. Using Prospector, they save time with plastic material selection by quickly and easily referencing technical information critical to the success of their products.

*"Prospector is absolutely the best and most well-known search engine for plastic raw materials in the world. We use Prospector every day – it's a real time saver!"*

– Birgit Elvardt Bader, Production Manager, Micotron

#### Power Searches

**Property Search** – select plastics by 500 key properties and design parameters.

**Alternative Resins Search** – find replacement plastics within minutes.

**Automotive Plastics Search** – easily locate automotive approved plastics.

**Curve Data** – view, overlay and export curve data.



### Material Data Management – [www.ides.com/datasheets](http://www.ides.com/datasheets)

With our data management services, plastic suppliers and distributors can have custom search interfaces available on their website for their customers, website visitors, sales and customer service teams. These provide intuitive ways to find and view technical data sheets for their products.

*"With UL IDES data services, our website now displays the most current information on the products we distribute and links to our backend RFQ and sales order system, adding both value and service for our customers."*

– Kevin Chase, Owner & President, Chase Plastics



### Advertising – [www.ides.com/advertise](http://www.ides.com/advertise)

Reach 365,000 pre-qualified plastics professionals and generate leads with proven techniques. Electronic newsletter insertions, sponsored webinars and powerful online ads are available to make the most of your lead-generation program.



For more information, call: 800.788.4668 or 307.742.9227 ext. 220