



SHINPET 5015X

TECHNICAL SPECIFICATION

2004.06.01

PROPERTY	UNIT	TEST METHOD	VALUE
TYPE			Copolymer
I.V.	[η]	ASTM D-2857	0.84±0.02
MOISTURE CONTENT	wt %	ASTM D-4019	<0.5
MELTING POINT	° C	ASTM D-3418	246±4
COLOR (b)		JIS Z 8722	-1.0±2.0
Acid Value (COOH)	10 ⁻⁶ equ/g	Zimmer PV.07013.4	30MAX
A.A. CONTENT	ppm	CELANESE	<1
PELLET SHAPE			OVAL
BULK DENSITY	g / cm ³	ASTM D-792	0.9±0.1
PACKING	Kg / Bag		1100
MOLDING TEMP.	° C		275-290

* NOTE : 1.RECOMMENED DRYING TEMP. / TIME
160 ~ 170 ° C / 5 ~ 7 hours .

Properties reported here are typical of average lots. Makes no representation that the material in any particular shipment will conform exactly to the values given. Neither SSFC nor its marketing affiliates shall be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.