## TRICOLENE **HDB5502**

**High Density Polyethylene** 

777 Post Oak Blvd, Suite 550, Houston TX, USA - 77056

**+1-713-963-0066** 

www.triconenergy.com





## PRODUCT DESCRIPTION

This type of HDPE is a copolymer of ethylene and 1-hexene

PROCESSING METHODS	CHARACTERISTICS	API	PLICATIONS	
(Co)Extrusion Blow Molding Sheet (Co)Extrusion	Good Stiffness Good Processability	Pha	usehold and Industrial Chemical Containers armaceutical Containers ad Packaging Containers	
RESIN PROPERTIES	TEST METHOD	VALUES, ENGLISH UNITS	VALUES, INTERNATIONAL UNITS	
Melt Flow Rate 2.16 kgf/190 °C MFR <sub>2</sub> Density 23 °C  Antioxidant Package	ASTM D1238 ASTM D1505 	<b>0.35</b> g/10 min <b>0.955</b> g/cm <sup>3</sup> <b>Yes</b>	<b>0.35</b> g/10 min <b>0.955</b> g/cm <sup>3</sup> <b>Yes</b>	
MECHANICAL PROPERTIES *	TEST METHOD	VALUES, ENGLISH UNITS	VALUES, INTERNATIONAL UNITS	
Tensile Strenght at Yield 2,0 in/min (50,8 mm/min), Type IV compression molded plaque	ASTM D638	<b>4,000</b> psi	<b>28</b> MPa	
<b>Tensile Elongation at Break</b> 2,0 in/min (50,8 mm/min), Type IV compression molded plaque	ASTM D638	600 %	600 %	
Flexural Modulus Initial Tangent - 0,051 in/min (1,3 mm/min)	ASTM D790A	<b>200,000</b> psi	<b>1,379</b> MPa	
OTHER PROPERTIES *	TEST METHOD	VALUES, ENGLISH UNITS	VALUES, INTERNATIONAL UNITS	
Environmental Stress Crack Resistance - ESCR Condition B: 100 % Igepal at 50 °C, F50	ASTM D1693	<b>24</b> h	<b>24</b> h	

<sup>\*</sup>The data presented here is true and accurate to the best of our knowledge. Likewise, the values are nominal and should not be taken as minimum or maximum specifications. No warranty, express or implied, is made regarding resin performance. The customer must validate these properties according to his own evaluations on his machine and in his laboratory.

## **REGULATORY COMPLIANCE**

This resin complies with the following FDA regulation: 21 CFR 177.1520: Olefinic Polymers. This regulation describes polyolefin resins that can be used safely for food packaging and preservation at low temperatures and at ambient temperatures. This resin is not designed for use in medical applications and should not be used