

# SABIC® PP 5052P

## PROVISIONAL DATA SHEET POLYPROPYLENE HOMOPOLYMER

### DESCRIPTION

SABIC® PP 5052P is a homopolymer which formulated with a low water-carry-over additives packages. It is suitable used for extrusion and thermoforming applications

### TYPICAL APPLICATIONS

SABIC® PP 5052P can be used for extrusion and thermoforming applications

### TYPICAL PROPERTY VALUES

Revision 20240925

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>POLYMER PROPERTIES <sup>(1)</sup></b>			
<b>Melt Flow Rate (MFR)</b>			
at 230°C and 2.16kg	1.8	g/10 min	ISO 1133
<b>MECHANICAL PROPERTIES <sup>(1)</sup></b>			
<b>Tensile Stress at Yield</b>	34	MPa	ISO 527-1/-2
<b>Tensile modulus</b>	1500	MPa	ISO 527

(1) Typical values, not to be construed as specific limits

### PROCESSING CONDITIONS

PP 5052P: Recommended melt temperature in the range of 190-240°C can be used.

### STORAGE AND HANDLING

Polypropylene resin should be stored in a manner to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably do not exceed 50°C. SABIC would not give warranty to bad storage conditions which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process PP resin within 6 months after delivery.

### DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.