

# MultiPoly™ IM9200

## High Density Polyethylene Resin

### Overview

MultiPoly™ IM9200 is a high-density polyethylene (HDPE) grade developed for injection molding. It delivers a strong balance of toughness, stress crack resistance, and processability, with a very narrow molecular weight distribution for consistent performance.

### Key Features & Benefits

- Excellent toughness and durability
- Strong environmental stress crack resistance
- Reliable processability for molders
- Narrow molecular weight distribution ensuring uniformity

### Typical Applications

- Housewares
- Toys
- Food containers
- Pails and similar molded products

Additive	- Antiblock: No	- Slip: No	- Processing Aid: No	
<b>Physical</b>		Nominal Value (English)	Nominal Value (SI)	Test Method
Density		0.954 g/cm <sup>3</sup>	0.954 g/cm	ASTM D792
Base Density <sup>1</sup>		0.954 g/cm <sup>3</sup>	0.954 g/cm	MFR Method
Melt Index (190°C/2.16 kg)		20 g/10 min	20 g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance (ESCR) 122°F (50°C), 100% Igepal, F50		< 3.00 hr	< 3.00 hr	ASTM D1693
<b>Mechanical</b>		Nominal Value (English)	Nominal Value (SI)	Test Method
<b>TENSILE STRENGTH<sup>2</sup></b>				ASTM D638
Yield		4100 psi	28.3 MPa	
Break		2000 psi	13.8 MPa	
<b>TENSILE ELONGATION</b>				ASTM D638
Yield		7.0 %	7.0 %	
Break		250 %	250 %	
<b>FLEXURAL MODULUS - 2% SECANT</b>		167000 psi	1150 MPa	ASTM D790B
<b>Impact</b>		Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Impact Strength <sup>2</sup>		20.0 ft-lb/in <sup>2</sup>	42.0 kJ/m <sup>2</sup>	ASTM D1822
<b>Hardness</b>		Nominal Value (English)	Nominal Value (SI)	Test Method
Durometer Hardness (Shore D)		57	57	ASTM D2240

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load 66 psi (0.45 MPa), Unannealed	163 °F	72.8 °C	ASTM D648
Brittleness Temperature	< -105 °F	< -76.1 °C	ASTM D746
Vicat Softening Temperature	261 °F	127 °C	ASTM D1525
Melting Temperature (DSC)	266t °F	130 °C	MFR Method
Peak Crystallization Temperature (DSC)	243t °F	117 °C	MFR Method

#### ADDITIONAL INFORMATION

Plaque molded and tested in accordance with ASTM D4976.

#### Notes

These are typical properties only and are not to be construed as specifications. Users should confirm results by their own tests.  
 1 Base density is estimated using the assumption that every 1000 ppm of anti block in the finished product raises the density of the polymer by 0.0006 g/cm<sup>3</sup>. Base density is the estimated density of the polymer if it did not contain any anti block.  
 2 Type S

## Compliance & Regulations

- FDA 21 CFR 177.1520 (c)3.2a
- FDA – DMF
- Canadian HPFB – No Objection
- EU Regulation No 10/2011

#### Disclaimer

The information provided herein is offered in good faith and without charge, but without guarantee or warranty of any kind, express or implied, including warranties of merchantability or fitness for a particular purpose. Conditions of use are beyond the control of Multi Trade Group, Inc.; therefore, it is the responsibility of the user to determine suitability for their application and to ensure safe handling and compliance with applicable laws and regulations. Multi Trade Group, Inc. assumes no liability for damages, injuries, or losses arising from the use of this product or information. This document relates only to the product designated and is not valid when used in combination with other materials or processes, nor does it imply freedom from patent or trademark infringement.